UNCLASS	SIFIED	F VILLE A CO	MASTER COPY	' _ '	FOR REPI	RODUCT	CION PU	RPOSES	
		2 360	REPORT DOCUM	MENTATION	PAGE				
1a. REPORT S	ECURITY CLASS	IFICATION		16. RESTRICTIVE	MARKINGS		H. I		
Unclassified 2a. SECURITY CLASSIFICATION AUTHORITY				3 DISTRIBUTION/AVAILABILITY OF REPORT					
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE				Approved for public release; distribution unlimited.					
4. PERFORMING ORGANIZATION REPORT NUMBER(S)				5. MONITORING ORGANIZATION REPORT NUMBER(S)					
	4		ARO 22388.8-MS						
6a. NAME OF	PERFORMING	ORGANIZATION	7a. NAME OF MONITORING ORGANIZATION						
North Carolina State University (If applicable)				U. S. Army Research Office					
6c. ADDRESS	(City, State, and	d ZIP Code)	7b. ADDRESS (City, State, and ZIP Code)						
Dalaidh	NC 2760	15			ox 12211				
Raleigh, NC 27695-				Research Triangle Park, NC 27709-2211					
8a. NAME OF FUNDING/SPONSORING 8b. OFFICE SYMBOL (If applicable)				9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER					
	Army Resear	ch Office	(If applicable)	DAA629-85-K-0128					
8c. ADDRESS	(City, State, and	ZIP Code)		10. SOURCE OF FUNDING NUMBERS					
P. O. Box 12211				PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.		WORK UNIT ACCESSION NO.	
Researc	ch Triangle	Park, NC 27	7709-2211						
	lude Security C				<u> </u>				
<u>the Me</u>	<u>chanical</u> F	ent of Epoxy F Properties.	Resins to I. Re Unclassifie	duce Moistur d.	e Sensitivii	ty and	III.	Improve	
12. PERSONAI	L AUTHOR(S)	Richard D. Gi	lbert and Raymon	nd E. Fornes					
13a. TYPE OF REPORT 13b. TIME COVERED FROM 05/01/85TO 07/31/89				14. DATE OF REPORT (Year, Month, Day) 15. PAGE COUNT 09/15/89					
16. SUPPLEME	ENTARY NOTAT	ON The view.	opinions and/or	findings co	ntained in 1	this r	eport	are those	
of the a	uthor(s) a	ind should not	be construed a	s an officia	l Department	t of t	he Ara	y position,	
17.	COSATI	CODES		continue on reverse if necessary and identify by block number)					
FIELD	GROUP	SUB-GROUP	Reduced Mois	sture Absorption - Epoxy Resins (Unclassified)					
									
19. ABSTRACT	(Continue on i	reverse if necessary	and identify by block n	umber)					
on comp attract blockir moistur to curi up to 6	posite med tion betwee ng the fund re absorpti ing permits 55% without	hanical prope en residual fu ctional groups ion as much as s in situ bloo t affecting th	er composites ab rties. The mois unctional groups s with various r s 75%. Marked i cking of the fun ne elastic modul ly unaffected.	ture absorpt on the epox eactants dec socyanates i ctional grou us. The res	tion results y resin mole reases the e ncorporated ps, reduces	from ecules epoxy into moist	the e and w resin the re ture ab but t	lectrostatic later, equilibrium sin prior sorption he stress-	
SUIGIII	propercies	are yelleral	iy unarrecteu. 🦿				D	TIC	
							FI	ECTE	
							SE	P 1 3 1989	
		LITY OF ABSTRACT		21. ABSTRACT SEC		ATIO	VV.		
	SIFIED/UNLIMITI	ED SAME AS R	PT. DTIC USERS	Und 22b. TELEPHONE (F	classified	1 220 0	SEELCE SEVE	MROL	
ZZE. NAME U	A KESLONZIRFF	INUIVIDUAL		220. IELEPHUNE (/	TRUTUE ALES CODE	، احدد ر	14 JULY 1	NUOL	

DD FORM 1473, 84 MAR

83 APR edition may be used until exhausted. All other editions are obsolete.

SECURITY CLASSIFICATION OF THIS PAGE UNGASSIFUE 68

Chemical Treatment of Epoxy Resins to I. Reduce Moisture Absorption and II. Improve the Mechanical Properties


Richard D. Gilbert and Raymond E. Fornes

September 15, 1989

Contract/Grant Number DAAG29 - 85 - K - 0128

North Carolina State University Raleigh, North Carolina 27695

Approved for Public Release; Distribution Unlimited





Statement of Problem

Epoxy resin/graphite fiber composites absorb significant amounts (~ 4%) of water which causes a decrease in the epoxy resin Tg, plasticization, microcracking, delamination, and resin-fiber debonding, resulting in a serious property loss.

The epoxy resin at its optimum degree of cure contains numerous functional groups (hydroxyl, amine, epoxide, sulfone) and the electrostatic attraction between these groups and water provide the driving force for water absorption. The amount of water uptake is determined by the unoccupied volume of the epoxy which is a function of the degree of cure. It was proposed to study the effect of blocking the functional groups, by chemical reaction with suitable reactants, on the moisture absorption. Reduction of the moisture absorption would improve mechanical properties. It was also proposed to study the use of carboxylic terminated elastomers to obtain a better property balance at higher degrees of cure.

Summary of Important Results

- 1. Employing thin films of the epoxy resin, it was shown by infrared spectroscopy and differential scanning calorimetry, that silylation, carbanilation, and/or cyanoethylation of residual hydroxyl, amine, and epoxy groups occurs.
- 2. Reductions in equilibrium moisture absorptions up to 75 percent were obtained.
- 3. Moisture uptake by the epoxy resin exhibits Fickian behavior at 30, 45, 55, and 70°C. The diffusion coefficient, D, increased from 30° to 55°C but decreased at 70°C, attributed to a reaction of water with residual oxirane groups.
- 4. Sorption of isocyanates essentially follows Fickian behavior.
- 5. Moisture diffusion of the films after blocking the residual functional groups by cyanoethylation or carbanilation exhibits Fickian behavior. At 30°C, D values are significantly higher for reacted films. At 70°C, the value of D is unchanged for cyanoethylated films, but D values are significantly lower for films reacted with isocyante blocking agents compared with the epoxy resin.
- 6. Blocking the residual functional groups of the epoxy resin with fluorinated aromatic reagents reduced the equilibrium moisture absorption by as much as 75%. Pentafluorobenzoyl chloride is a more efficient blocking reagent than fluorinated isocyanates. 2,4-Difluorophenyl isocyanate is a more effective blocking reagent than the trifluoromethylphenyl isocyanates due to its higher reactivity.

- 7. Several masked isocyanates were synthesized with variations in both the isocyanate type and masking group and were characterized by elemental analysis and NMR spectroscopy and determination of their unblocking temperatures. Those with unblocking temperatures in the 120–130°C range were incorporated into the epoxy resin prior to curing to provide in situ blocking of residual function groups in the epoxy resin. Infrared spectroscopy and differential scanning calorimetry demonstrated the residual functional groups were reacted. Reduction in equilibrium moisture absorptions as high as 65% were obtained, depending on the masked isocyante.
- 8. Dynamic mechanical analysis studies showed the Tg of the epoxy resin is lowered by incorporation of the masked isocyanate, but the elastic modulus is relatively unchanged at temperatures below Tg.
- 9. Stress-strain studies of the epoxy resins after curing in the presence of the masked isocyanates are relatively unaffected by incorporation of the masked isocyanate, demonstrating this approach is a practical technique for lowering the equilibrium moisture absorption of epoxy resins.
- 10. High resolution ¹³C-CP/MAS NMR was used to follow the reactions of the residual functional groups with the masked isocyanates and to identify intermediates and by-products.

Publications

"Reduction in the Moisture Absorption of Cured MY 720/DDS Epoxy Resin," by C. M. Fisher, R. D. Gilbert, R. E. Fornes, and J. D. Memory, J. Polym. Sci., Polym. Chem. Ed., 1985, 23, 2931.

"Chemical Modification of Cured MY 720/DDS Epoxy Resins Using Fluorinated Aromatic Compounds to Reduce Moisture Sensitivity," by H.-P. Hu, R. D. Gilbert, and R. E. Frances, J. Polym. Sci., Polym. Chem. Ed., 1987, 25, 1235.

"Sorption and Transport Properties of MY 720/DDS Epoxy Reacted with Blocking Reagents," by B. K. Kelly, R. D. Gilbert, R. E. Fornes, and V. T. Stannett, J. Polym. Sci., Polym. Phys., 1988, 26, 126.

"The Effect of Masked Isocyanates on the Moisture Absorption of MY 720/DDS Epoxy Resin, by S. V. Lonikar, N. Rungsimuntakul, R. D. Gilbert, and R. E. Fornes, J. Polym. Sci., Polym. Chem. Ed., Accepted for Publication.

"Solid State CP MAS ¹³C NMR Studies of the Reaction of an Epoxy Resin with Masked Isocyanates," by S. S. Sankar, S. V. Lonikar, R. D. Gilbert, R. E. Fornes, and E. O. Stejskal, *J. Polym. Sci., Polym. Phys.*, Accepted for Publication.

"Sorption and Transport Properties of MY 720/DDS Epoxy Reacted with Blocking Reagents," Proceedings of the Fifth International Joint Military/Government-Industry Symposium on Structural Adhesive Bonding, pp. 471-479 (Nov. 3-5, 1987). B. K. Kelly, R. D. Gilbert, R. E. Fornes, S. Lonikar, and N. Rungsimuntakul.

Participating Scientific Personnel

R. E. Fornes		Department of Physics				
	R. D. Gilbert	Department of Textile Engineering, Chemistry, and Science				
	J. D. Memory	Department of Physics				
	HP. Hu	Post-doctoral Research Associate				
	S. V. Lonikar	Post-doctoral Research Associate				
	C. M. Fisher	Graduate student; Ph.D. awarded 1985				
	B. K. Kelly	Graduate student; M.S. awarded 1986				
	N. Rungsimuntakul	Graduate student, Ph.D. expected November, 1989				

The view, opinions, and/or findings contained in this report are those of the authors and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.